

# Sun Tech Coatings Mfg.

"Manufacturers of Quality Elastomeric Products"

5322 W Missouri Ave  
Glendale AZ 85301



Office (623)842-0690  
Fax (623)842-1044

## Sun Tech Coatings Deck-Coat Non-Skid Elastomeric Coating

**Product Name:** DECK-COAT

**Manufacturer:**

Sun Tech Coatings Mfg.  
5322 W. Missouri Ave  
Glendale AZ 85301  
Phone: 623-842-0690  
Fax: 623-842-1044

**Packaging:** 2 and 5 Gallon

**Product Description:** DECK-COAT is water based 100% acrylic fire resistant. Non-skid, waterproof, textured floor and deck coating system. Designed to protect and beautify a wide variety of walking surfaces from damage and deterioration due to weather and pedestrian traffic. DECK-COAT is a non-toxic and is environmentally safe.

**Colors:** DECK-COAT is available in 11 beautiful decorative stock colors. Custom colors and textures are available to coordinate with existing color combinations.

**Properties:** Solids by weight – 66- 70%  
Drying time at 75°F – to  
Touch – 30 Minutes  
Recoat- 5-6 Hours  
V.O.C – 70 grams per liter  
Solvent – Water  
Shelf Life- 1 Year

**Surface Preparation:** Surface must be clean and dry, free of dust, oil drippings, oil paint and other foreign materials. Power washing is recommended. Allow to dry completely (24hours) before applying DECK-COAT. Concrete should be acid

etched, metal surfaces should be rinsed with a 50/50 solution of water and vinegar.

**Application Instructions:** Mix DECK-COAT prior to and during use. DECK-COAT should be applied in the cooler hours of the day. Application in direct sunlight may result in rapid water loss causing application difficulties. Under these conditions you may add 1 to 3 cups of water to 1 gallon of DECK-COAT. Apply using 4" or larger paint brush or 9" roller. (Water dampen roller before using. Shake off excess water.) Spread evenly in north south or east west direction. Allow the first coat to dry 5-6 hours before applying second coat. Finish in one direction for even color consistency. (For best results pretreat the deck surface with SUR-SEAL 3000 according to label directions).

**Coverage:** 90-120 Sq. Ft. per Gallon

**NOTE:** Coverage rate is listed in square feet per gallon and is approximate. Actual rates will vary depending upon surface porosity and method of application.

**Clean-Up:** Clean-up with soap and water

**Drying Time:** Protect newly coated surfaces for 24 hours before light traffic, 48 hours before heavy traffic.

**NOTE:** With high humidity (75 % or higher) drying time should be doubled.

*Contact mfg. for application or technical assistance.*

**Surface Care:** DECK-COAT should be cleaned only after it has cured for 3 weeks. Use a solution of water and T.S.P or a mild detergent and scrub lightly with a soft

bristle brush. Rinse thoroughly with clean water.

**Product Limitations:** DECK-COAT

should not be applied over cold tar emulsion coatings. Apply to surfaces that permit water runoff. Apply this coating only when air temperatures are above 50°F DECK COAT should not be used as a below grade or submerged water proofing material. It should not be applied over dirty, oily, greasy, or waxy surfaces.

**NOTE:** Light colors may more readily stain or pick up dirt.

*Keep out of reach of children.* Avoid prolonged contact with skin.

Do not allow to freeze. Store between 50°F and 100°F. Solidification and destruction of this product will be the result of freezing.

*Caution: Do not take internally. If swallowed do not induce vomiting. Seek medical attention immediately. If contact with eyes occur flush thoroughly with water and seek medical attention immediately. Avoid prolonged or repeated contact with skin irritation or sensitivity. Wear gloves.*

**Limited Warranty:** Sun Tech warrants this product is free of any defects in manufacturing. This warranty is limited to the replacement of the product at the expense of the company, when such product proves to be defective in manufacturing. Neither Sun Tech the seller shall be liable for the cost of the labor or direct, incidental, or consequential damages. This warranty guarantee is in lieu of the implied warranty of merchantability and all other warranties expressed or implied.